

Amodel® AT-6130 HS

polyphthalamide

Amodel® AT-6130 HS is a 30% glass-reinforced, toughened polyphthalamide (PPA) resin that has more elongation than other 30% glass-reinforced grades of Amodel® resin. This grade was developed for automotive snap-fit electronic connectors. It offers high flow and short molding cycles. The processing window is relatively broad and mold temperatures as low as 150°F (65°C) can be used.

- Black: AT-6130 HS BK 324
- Natural: AT-6130 HS NT

General

| | | | |
|---------------------------|---|--|--|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East • Asia Pacific | • Europe • Latin America | • North America |
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight | | |
| Additive | • Heat Stabilizer • Impact Modifier | • Lubricant • Mold Release | |
| Features | • Good Chemical Resistance • Good Flow • Good Wear Resistance • Heat Stabilized | • High Heat Resistance • High Strength • Hot Water Moldability • Impact Modified | • Low Friction • Lubricated |
| Uses | • Automotive Applications • Automotive Electronics • Automotive Under the Hood • Bearings • Connectors | • Fuel Lines • General Purpose • Housings • Industrial Applications • Industrial Parts | • Lawn and Garden Equipment • Machine/Mechanical Parts • Metal Replacement • Valves/Valve Parts |
| RoHS Compliance | • RoHS Compliant | | |
| Automotive Specifications | <ul style="list-style-type: none"> • ASTM D4000 PPA0123 G30 KD150 KN080 PM095 PN095 YI255 LD002 Color: BK-324 Black • ASTM D4000 PPA0123 G30 KD150 KN080 PM095 PN095 YI255 LD002 Color: NT Natural • ASTM D6779 PA103G30 • DELPHI MS 5218 Color: BK-324 Black • DELPHI MS 5218 Color: NT Natural • GM GMP.PPA.017 Color: BK-324 Black • GM GMP.PPA.017 Color: NT Natural • GM GMW16363P-PPA-GF30 Color: Black • GM GMW16363P-PPA-GF30 Color: Natural • ISO 1874-PA 6T/66-HI, MH, 11-090, GF30 | | |
| Appearance | • Black | • Natural Color | |
| Forms | • Pellets | | |
| Processing Method | • Water-Heated Mold Injection Molding | | |

| Physical | Dry | Conditioned Unit | Test method |
|----------|------|----------------------|-------------|
| Density | 1.34 | -- g/cm ³ | ISO 1183/A |

Amodel® AT-6130 HS

polyphthalamide

| Physical | Dry | Conditioned | Unit | Test method |
|--------------------------------|-----------------|--------------------|-------------------|--------------------|
| Molding Shrinkage | | | | ASTM D955 |
| Flow | 0.50 | -- | % | |
| Across Flow | 0.80 | -- | % | |
| Water Absorption (24 hr) | 0.15 | -- | % | ASTM D570 |
| Mechanical | Dry | Conditioned | Unit | Test method |
| Tensile Modulus | 9310 | -- | MPa | ISO 527-2 |
| Tensile Strength | | | | |
| Break | 167 | -- | MPa | ASTM D638 |
| Break | 170 | -- | MPa | ISO 527-2 |
| Tensile Elongation | | | | |
| Break | 3.2 | -- | % | ASTM D638 |
| Break | 3.3 | -- | % | ISO 527-2 |
| Flexural Modulus | | | | |
| -- | 7860 | -- | MPa | ASTM D790 |
| -- | 7580 | -- | MPa | ISO 178 |
| Flexural Stress | | | | |
| -- | 225 | -- | MPa | ISO 178 |
| Yield | 236 | -- | MPa | ASTM D790 |
| Impact | Dry | Conditioned | Unit | Test method |
| Charpy Notched Impact Strength | 13 | -- | kJ/m ² | ISO 179/1eA |
| Notched Izod Impact | 130 | -- | J/m | ASTM D256 |
| Unnotched Izod Impact | 1400 | -- | J/m | ASTM D256 |
| Thermal | Dry | Conditioned | Unit | Test method |
| Heat Deflection Temperature | | | | |
| 0.45 MPa, Unannealed | 298 | -- | °C | ISO 75-2/B |
| 1.8 MPa, Unannealed | 276 | -- | °C | ISO 75-2/A |
| Melting Temperature | | | | |
| -- | 310 | -- | °C | ISO 11357-3 |
| -- | 306 | -- | °C | ASTM D3418 |
| Injection | Dry Unit | | | |
| Drying Temperature | 121 °C | | | |
| Drying Time | 4.0 hr | | | |
| Suggested Max Moisture | 0.15 % | | | |
| Rear Temperature | 316 to 324 °C | | | |
| Front Temperature | 327 to 332 °C | | | |
| Processing (Melt) Temp | 321 to 335 °C | | | |
| Mold Temperature | 65.6 to 93.3 °C | | | |
| Injection Rate | Fast | | | |

Amodel® AT-6130 HS

polyphthalamide


Injection Notes

Injection pressure between 2-4 in/sec (5-10 cm/sec). Adjust the holding pressure to one-half the injection pressure.

Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

Isothermal Stress vs. Strain (ISO 11403-1)



Data Notes
(1) - ISO Protocol

Amodel® AT-6130 HS

polyphthalamide

Notes

Typical properties: these are not to be construed as specifications.

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2016 Solvay Specialty Polymers. All rights reserved.

